

# TEST REPORT

G T I T E S T I N G L A B O R A T O R I E S  
1700 South Mount Prospect Road | Des Plaines, Illinois 60018

**Brian K. Spillar**  
Manager, Industrial Testing Services  
T: 847 768 0658 F: 847 768 0569  
Brian.Spillar@gastechnology.org



IFC Techprocomplect LLC  
1, 62, Starokaluzhskoye Shosse  
Moscow, 117630, Russia  
Ph. +7 495 974 7008

3/31/2009

Reference: Test results for TIAL-M80 backing: Our Report 081659.

We have completed testing on the following materials submitted to our laboratory.

Material Name: Backing layer of TIAL-M80 heat shrinkable wrap-around sleeve.  
Test Method: ASTM D257-1999\* D-C Resistance of Insulating Materials  
Quantity of specimens: 3  
Specimen Dimensions: 4" x 4" 0.051" thick \*\*.  
Test Temperature °C: 23°C  
Applied Voltage: 500V

When tested in accordance with ASTM D257-1999 the following results were obtained:

**Volume Resistivity  $>1.8 \times 10^{17} \Omega \cdot \text{mm}$**

A handwritten signature in black ink that reads 'Brian K. Spillar'.

Brian K. Spillar  
Manager, Industrial Testing Services

Neither GTI nor any person acting on behalf of GTI assumes any liability with respect to the use of, or for damages resulting from the use of, any information presented in this report.

\*Performed at a subcontracted A2LA accredited laboratory.

\*\* As manufactured thickness.